



Protective & Marine Coatings

ACROLON™ C237 ACRYLIC URETHANE SHEEN FINISH

FORMERLY KNOWN AS RESISTEX C237

Revised 11/2016 Issue 18

PRODUCT INFORMATION

PRODUCT DESCRIPTION

A high performance fast drying acrylic urethane sheen finish for use where long term exterior colour retention characteristics are required

RECOMMENDED USE

Material is suitable for use as final coat or coats in conjunction with epoxy or polyurethane based protective systems for new construction or maintenance purposes. Good tolerance to low temperature curing conditions. May also be used as an undercoat where a gloss finish is required

ENDORSEMENTS

Network Rail Item No. 7.3.1.

RECOMMENDED APPLICATION METHODS

Airless Spray
Conventional Spray
Brush
Roller

Recommended Thinner:

Cleanser/Thinner No 5 (for cleaning)
Cleanser/Thinner No15 (for thinning)

PRODUCT CHARACTERISTICS

Finish: Sheen

Flash Point: Base : 28°C Additive : 32°C

% Solids by Volume: 54 ± 2% (ASTM-D2697-91)

Pot Life: 6hrs @15°C 4hrs @ 23°C 2hrs @ 35°C

Colour Availability: Full range

VOC

405 gms/litre determined practically in accordance with UK Regulations PG6/23
443 gms/litre calculated from formulation to satisfy EC Solvent Emissions Directive
283 gms/kilo content by weight from formulation, to satisfy EC SED

RECOMMENDED THICKNESS

Dry film thickness	Wet film thickness	Theoretical coverage
50 microns	92 microns	10.8m ² /ltr*

*This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment. Film thickness will vary depending on actual use and specification

PRACTICAL APPLICATION RATES - MICRONS PER COAT

	Airless Spray	Conventional Spray	#Brush	#Roller
Dry	50*	50	20-40	20-40
Wet	92	**106	37-75	37-75

*Maximum sag tolerance with overlap typically 185µm wet (100µm dry) by airless spray.

**The conventional spray details relate to the paint after thinning 15% with Cleanser/Thinner No 15

The actual thickness within the quoted range will depend on many variables including ambient conditions, type of brush or roller used and operator expertise.

AVERAGE DRYING TIMES

	@ 15°C	@ 23°C	@ 35°C
To touch:	2½ hours	1½ hours	¾ hour
To recoat:	8 hours	6 hours	4 hours
To handle	24 hours	16 hours	10 hours

These figures are given as a guide only. Factors such as air movement and humidity must also be considered.

RECOMMENDED PRIMERS

Compatible with a wide range of Macropoxy, Dura-plate, Zinc Clad Epoxy Primers and Buildcoats.

RECOMMENDED TOPCOATS

Not normally required but indefinitely overcoatable with itself and other high performance topcoats.

PACKAGE

A two component material supplied in separate containers to be mixed prior to use.

Pack Size: 5 litre and 20 litre units when mixed

Mixing Ratio 9 parts base to 1 part additive by volume.

Weight: 1.63 kg/litre (may vary with shade)

Shelf Life: 12 months from date of manufacture or 'Use By' date where specified



Protective & Marine Coatings

ACROLON™ C237 ACRYLIC URETHANE SHEEN FINISH

FORMERLY KNOWN AS RESISTEX C237

Revised 11/2016 Issue 18

PRODUCT INFORMATION

SURFACE PREPARATION

Ensure surfaces to be coated are clean, dry and free from all surface contamination.

APPLICATION EQUIPMENT

Airless Spray

Nozzle Size : 0.38mm (15 thou)
Fan Angle : 80°
Operating Pressure : 140kg/cm² (2000 psi)

The airless spray details given above are intended as a guide only. Details such as fluid hose length and diameter, paint temperature and job shape and size all have an effect on the spray tip and operating pressure chosen. However, the operating pressure should be the lowest possible consistent with satisfactory atomisation. As conditions will vary from job to job, it is the applicators' responsibility to ensure that the equipment in use has been set up to give the best results. If in doubt Sherwin-Williams should be consulted.

Conventional Spray

Nozzle Size : 1.27mm (50 thou)
Atomising Pressure : 3.5kg/cm² (50 psi)
Fluid Pressure : 0.7-1.0kg/cm² (10-15 psi)

The details of atomising pressure, fluid pressure and nozzle size are given as a guide. It may be found that slight variations of pressure will provide optimum atomisation in some circumstances according to the set up in use. Atomising air pressure depends on the air cap in use and the fluid pressure depends on the length of line and direction of feed i.e. horizontal or vertical.

Acrolon C237 may be conventionally sprayed thinning up to 15% with Cleanser/Thinner No. 15

N.B. Thinning will affect VOC compliance.

Brush

The material is suitable for brush application. Application of more than one coat may be necessary to give equivalent dry film thickness to a single spray applied coat.

Roller

The material is suitable for roller application. Application of more than one coat may be necessary to give equivalent dry film thickness to a single spray applied coat.

APPLICATION CONDITIONS AND OVERCOATING

This material should preferably be applied at temperatures in excess of 10°C. In conditions of high relative humidity, ie 80-85% good ventilation conditions are essential. Substrate temperature shall be at least 3°C above the dew point and always above 0°C.

At application temperatures below 10°C, drying and curing times will be significantly extended, and spraying characteristics may be impaired.

Application at ambient air temperatures below 5°C is not recommended.

If it is desired to overcoat outside the times stated on the data sheet, please seek advice of Sherwin-Williams.

ADDITIONAL NOTES

Drying times, curing times and pot life should be considered as a guide only.

The curing reaction of the material commences immediately the two components are mixed, and since the reaction is dependent on temperature, the curing time and pot life will be approximately halved by a 10°C increase in temperature and doubled by a 10°C decrease in temperature.

Certain shades, for example yellows and reds, may require additional coats to achieve full opacity.

Numerical values quoted for physical data may vary slightly from batch to batch.

HEALTH & SAFETY

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

WARRANTY

Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.

The information detailed in this Data Sheet is liable to modification from time to time in the light of experience and of normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.